

Mapolene PPH350 is a homopolymer polypropylene resin designed for various general purpose injection molded applications such as closures, small appliances, housewares and toys. It contains a unique combination of stabilizers, which provides excellent processability with good stiffness, environmental stress crack resistance, heat performance and minimal odor & taste.

Mapolene PPH350

Polypropylene ~ Homopolymer	Melt Flow	35
General Purpose Injection Molding	Izod	0.4

Properties ¹	ASTM	Units	Value
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	g/10 min	35
Density	ASTM D1505	g/cm ³	.900
Tensile Strength at Yield (2 in/min)	ASTM D638	psi	4900
Flexural Modulus (1% Secant)	ASTM D790	psi	180,000
Izod Impact, Notched @73°	ASTM D256	ft-lb/in	0.4
Elongation at Yield	ASTM D638	%	8
Heat Deflection Temperature @66 psi	ASTM D648	°F	212

This material meets the Food and Drug Administration requirements of 21CFR 177.1520.

¹Properties will vary and are not to be used for specification purposes.

All inquiries regarding this data sheet should be addressed to: 1140 Route 22 East, Suite 109, Bridgewater, NJ 08807 • Phone 908.725.3133 • Fax 908.725.9677

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement, and Mass Polymers Corporation shall not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.