

Mapolon 6030 is a low melt flow, high impact polystyrene resin designed for the extrusion of sheet for POP (Point of Purchase) displays, deep draw thermoforming; blends with GPPS for disposable packaging, cups and plates.

Mapolon 6030

Polystyrene	Melt Flow	3.0
HIPS / Extrusion	Izod	2.0

Properties ¹	ASTM	Units	Value
Melt Flow Rate (200°C/5.0kg)	ASTM D1238	g/10 min	3.0
Izod Impact @73° F	ASTM D 256	ft-lb/in	2.0
Tensile Strength, Break	ASTM D 638	psi	3200
Tensile Modulus	ASTM D 638	psi	280,000
Flexural Modulus	ASTM D 790	psi	310,000
Vicat Softening Temp	ASTM D 1525	°F	210

This material meets the Food and Drug Administration requirements of 21CFR 177.1640.

¹Properties will vary and are not to be used for specification purposes.

All inquiries regarding this data sheet should be addressed to: 1140 Route 22 East, Suite 109, Bridgewater, NJ 08807 • Phone 908.725.3133 • Fax 908.725.9677

The information contained herein is based upon data believed to be reliable and relates only to the matters specifically contained herein. Although such information is, to the best of our knowledge and belief, accurate and reliable as of the date hereof, no representation, warranty (expressed or implied, of merchantability, fitness or otherwise), or guarantee is made as to the suitability, accuracy, reliability, or completeness of the information. It is the user's responsibility to satisfy itself as to the suitability, accuracy, reliability and completeness of such information for its particular use. There is no warranty against patent infringement, and Mass Polymers Corporation shall not be liable for any loss, damage, or injury that may occur from the use of this information. No statement herein shall be construed as an endorsement of any product or process.